

DESCRIPTION

- ADEX NOVATRIM mouldings are made of superior-quality PVC to achieve precise and durable architectural details on interior or exterior walls and ceilings.

Density
ASTM D792:
1.38
Hardness
ASTM D2240:
79
Pull Strength
ASTM D638:
42.1 Mpa (6,100 PSI)
Bending Strength
ASTM D790:
76 Mpa (11,000 PSI)
IZOD Impact
ASTM D256:
1,084 J/m (20.3 ft-lb/in.)
Stamping Resistance
ASTM D4226:
53.4 J/cm (1.2 in-lb/mil)
Thermal Expansion Coefficient
ASTM D696:
6.7 x 10 ⁻⁵ cm/cm/°C (3.7 x 10 ⁻⁵ in/in/°F)
Flammability (V-O)
UL 94:
0.750 mm [0.0295 in.]
Colour
Grey
Length
3.05 m (10 ft)

■	Properties
■	Test Method
■	Result

PRECAUTIONS

- NOVATRIM mouldings must be clean, and free of grease or oil before being painted. A light sanding of the NOVATRIM moulding may be necessary to ensure proper adhesion.

SUBSTRATE ATTACHMENT

- On gypsum or cement boards, use appropriate length stainless-steel staples, set 200 mm (8 in.) apart, on both sides of the moulding.
- On polyisocyanurate boards, use "Trim-Tac" fasteners, set 200 mm (8 in.) apart on both sides of the moulding.
- Do not use adhesive to fasten NOVATRIM mouldings to the substrate.
- Fibreglass mesh embedded in acrylic base coat must always overlap the NOVATRIM mouldings. Ensure that the base coat adequately penetrates the perforations in the NOVATRIM moulding flanges.

LIMITATIONS

- NOVATRIM mouldings are only compatible with acrylic emulsion paints.
- Use of dark colours is not recommended.
- All NOVATRIM moulding joints must be treated with an appropriate sealant in order to ensure water tightness.

RESTRICTIONS

- Do not apply textured acrylic coatings to surfaces on which caulking will be installed.
- Do not install textured acrylic coatings to the inside of "V"-Groove expansion joints 3323 and decorative moulding #3322.

This document contains current information on the product. It is only provided as a guide and is subject to modifications at any time without notice. ADEX Systems Inc. reserves the right to make any modification according to technological progress. Specialised designers, architects, engineers or other professionals that choose to make any use of this information bear the complete responsibility, whatever it be, direct or indirect, that could follow from such use. ADEX Systems Inc. does not bear any responsibility that could give way to damages, defaults, defects, deficiencies, prejudices, loss or decrease of profit, be they direct or indirect, resulting from such use of this information by specialised designers, architects, engineers or other professionals. Please refer to www.adex.ca for the latest version of this document.

August 2016